

Glo-Bright Printable Photoluminescent test results

Glo Brite® Test results according to DIN 67510 Part 1 Standard:-

1,000 Lux Xenon lamp for 5 minutes at 22°C

All values in mcd/m² (luminance in millicandelas per square metre)

Glo Brite® or PSPA Class	2 mins	10 mins	30 mins	60 mins
Class B	210	50	15	7
3M VP1587-30	-	30	-	6
3M VP1587-50	-	50	-	8
Ritrama RI-459	-	99	-	14
Glo Bright 7535	641	119	35.4	12.4

Test results dated 12/07/2021

Version 1 16/01/2023