

STRIPFLOCK PRO™

SPECIFICATIONS

	Composition	Average Thickness	Carrier	Oeko-Tex	Certifications
Stripflock™ Pro standard colors*	PVC	650 microns	Adhesive Polyester	class I	 OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 18.HIT.56690 HOHENSTEIN HTTI REACH n° 1907/2006/EU
Stripflock™ Pro fluo colors	PU	620 microns		class II	 OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 19.HIT.98675 HOHENSTEIN HTTI VEGANOK AZIENDA N. 1004

*Stripflock Pro black Oeko-Tex standard 100 class II

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	60°	60 gf	15 cm/sec	15 seconds	155°C (311°F)	Medium (2,5/3,5 bar)	warm

- Mirror cut the design
- Weed excess material
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier warm

PRODUCT HIGHLIGHTS

- velvet touch
- embroidery look

NOTE: Stripflock Pro cannot be layered on itself. We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 60°C, inside-out	YES inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com
For further information, please contact our sales office: info@siser.it



Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246

