

SUBLITHIN MATT LT

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	110 microns	Non adhesive polyester	    

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
textiles colored with sublimation inks	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	80 gf	20 cm/sec	15 seconds	135°C (275°F)	Medium (2,5-3,0 bar)	hot

- Print, Cut and peel off excess material
- Remove the print from the support with the help of TTD Easy
- Place the decoration on the fabric
- Apply following the recommended parameters
- Remove the TTD while hot

PRODUCT HIGHLIGHTS

- Anti migration barrier
- Suitable for sublimation dyed fabrics
- Low temperature transfer

NOTE: Given the large number of sublimation inks and printers, we highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 40°C, best inside-out	NO	NO	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it



Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246



Management System
ISO 9001:2015
ISO 14001:2015
www.tuv.com
ID 9105027958

